

ATI 17-4-MIL™ Precipitation Hardening Alloy

GENERAL PROPERTIES

ATI Defense's ATI 17-4-MIL™ Precipitation Hardening Alloy (S17400), Type 630, is a chromium-nickel-copper precipitation hardening stainless steel used for applications requiring high strength and a moderate level of corrosion resistance. High strength is maintained to approximately 600°F (316°C).

The S17400 alloy is martensitic in structure in the annealed condition and is further strengthened by a low temperature treatment which precipitates a copper containing phase in the alloy. In comparison to many alloys in the precipitation hardening family, the S17400 alloy requires a simple heat treatment; a one step process conducted at a temperature in the range 900°F (482°C) to 1150°F (621°C) depending on the combination of strength and toughness desired. A wide range of properties can be produced by this one step heat treatment. Heat treatment in the 900°F (482°C) range produces highest strength, although slightly less than that of alloys like S17700 or S15700. The latter precipitation hardening alloys generally require more steps to complete heat treatment.

FORMS AND CONDITIONS

The ATI Defense ATI 17-4-MIL™ Precipitation Hardening Alloy is furnished as plate and long products. In all forms, the material is furnished in the annealed condition.

SPECIFICATIONS

The ATI 17-4-MIL™ Precipitation Hardening Alloy (S17400) is covered by the following wrought product specifications.

Element	Typical Composition (Weight Percent)
Carbon	0.04
Manganese	0.40
Phosphorus	0.020
Sulfur	0.005
Silicon	0.50
Chromium	15.50
Nickel	4.50
Columbium + Tantalum	0.30
Copper	3.50
Iron	Balance

Specification	Product Form
AMS 5604	Sheet, Strip and Plate
AMS 5643	Bars, Forgings, Tubing and Rings
AMS 5825	Welding Wire
AMS 5827	Welding Electrodes
AMS 7474	Bolts
ASTM A 564 ASTM SA 564	Bars, Wire and Shapes
ASTM A 693 ASME SA 693	Sheet, Plate and Strip
ASTM A 705 ASME SA 705	Forgings

Data are typical and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those herein. Copyright © 2008 Allegheny Technologies. ATI 17-4-MIL™ is a trademark of ATI Properties, Inc. Patent applications pending.

CORROSION AND OXIDATION RESISTANCE

Tests have shown that the corrosion resistance of ATI 17-4-MIL™ Precipitation Hardening Alloy is comparable to that of Type 304 stainless steel in most media. In general, the corrosion resistance of ATI 17-4-MIL™ alloy is superior to that of the hardenable 400 series stainless steels.

As with other precipitation hardening alloys, ATI 17-4-MIL™ Precipitation Hardening Alloy is more susceptible to stress corrosion cracking at peak strength. Consequently, in applications in which chloride stress corrosion cracking is a possibility, the material should be precipitation hardened to produce the lowest hardness compatible with the intended end use. This is done by heat treating at the highest temperature which will produce suitable minimum properties.

Material in the annealed condition should not generally be put into service. In this condition, the material has an untempered martensite structure and is less ductile than aged material. The untempered martensite may be subject to unpredictable brittle fractures. In corrosive environments, the untempered martensite is more sensitive to embrittling phenomena such as hydrogen embrittlement than material which has had one of the precipitation hardening heat treatments. Similarly, untempered martensite is more sensitive to chloride stress corrosion cracking than material in which the martensite has been tempered.

The oxidation resistance of the ATI 17-4-MIL™ alloy is superior to that of 12 percent chromium alloys like Type 410, but slightly inferior to that of Type 430. Precipitation hardening will produce surface oxidation.

PHYSICAL PROPERTIES

	Condition A	Condition H 900	Condition H 1075	Condition H 1150
Density lb / in ³ g / cm ³	0.280 7.75	0.282 7.81	0.283 7.83	0.284 7.86
Linear Coefficient of Thermal Expansion Units of				
10-6 / °F				
(10-6 / °C)				
Temperature Range				
-100°F to +70°F (-73°C to +21°C)		5.8 (10.4)	6.0 (10.8)	6.1 (11.0)
+70°F to 800°F (+21°C to +427°C)	6.3 (11.3)	6.5 (11.7)	6.8 (12.2)	7.2 (13.0)
Magnetic Permeability	Strongly Ferromagnetic in all Conditions			
Thermal Conductivity				
Btu - ft / hr -ft ² F				
(W / m - K)				
70 - 212°F (21 - 100°C)	10.6 (18.3)	10.3 (17.8)		
70 - 932°F (21 - 500°C)	13.1 (22.7)	13.1 (22.7)		
Electrical Resistivity microhm-cm	98	77	80	86

Data are typical and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those herein. Copyright © 2008 Allegheny Technologies. ATI 17-4-MIL™ is a trademark of ATI Properties, Inc. Patent applications pending.

ATI 17-4-MIL™ Precipitation Hardening Alloy

MECHANICAL PROPERTIES

Condition	A	H 900	H 1075	H 1150
Modulus of Elasticity				
10⁶ psi (GPa)	28.5 (196)	28.5 (196)	28.5 (196)	28.5 (196)
Modulus of Rigidity				
10⁶ psi (GPa)	11.2 (77.2)	11.2 (77.2)	11.2 (77.2)	11.2 (77.2)

Condition	A	H 900	H 1075	H 1150
0.2% Offset Yield Strength				
psi (MPa)	110,000 760	180,000 1,240	135,000 930	125,000 860
Ultimate Tensile Strength				
psi (MPa)	150,000 1,030	195,000 1,340	155,000 1,070	145,000 1,000
Elongation (percentage in 2")	8	10	10	10
Hardness Rockwell C Scale	33	43	31	28

Room temperature tensile properties can vary substantially with heat treatment in the 900°F (482°C) to 1150°F (621°C) range. Values shown to the right are typical room temperature properties which could be expected for

SUMMARY OF HEAT TREATING ATI 17-4-MIL™ ALLOY

Minimum Properties Specified in Aerospace Material Specification (AMS) 5604				
Heat Treat to Produce Martensitic Structure	Precipitation Heat Treatment to Produce Desired Strength			
	Precipitation Hardening Heat Treatment	Yield Strength ps (MPa)	Tensile Strength psi (MPa)	Hardness Rc
Solution Heat Treatment at 1950°F (1066°C) Condition A <i>(This is the condition furnished by ATI Defense)</i>	900°F (482°C) 60 minutes Condition H 900	170,000 (1170)	190,000 (1310)	40 to 47
	925°F (496°C) 4 Hours Condition H 925	155,000 (1070)	170,000 (1170)	38 to 45
	1025°F (552°C) 4 Hours Condition H 1025	145,000 (1000)	155,000 (1070)	35 to 42
	1075°F (579°C) 4 Hours Condition H 1075	125,000 (860)	145,000 (1000)	33 to 39
	1100°F (593°C) 4 Hours Condition H 1100	115,000 (790)	140,000 (965)	32 to 38
	1150°F (621°C) 4 Hours Condition H 1150	105,000 (725)	135,000 (930)	28 to 37
	1400°F (760°C) 2 Hours + 1150°F (621°C) 4 Hours Condition H 1150-M from SA 693	75,000 (515)	115,000 (790)	26 to 36

Data are typical and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those herein. Copyright © 2008 Allegheny Technologies. ATI 17-4-MIL is a trademark of ATI Properties, Inc. Patent applications pending.

HEAT TREATMENT

The ATI 17-4-MIL™ Precipitation Hardening Alloy is furnished in the annealed condition. This is also called the solution heat treated condition, or Condition A. Annealing is conducted by heat treating at approximately 1900°F (1040°C) to 1950°F (1065°C) and cooling to room temperature. In this condition, the material possesses a martensitic structure. As a martensitic structure, the ATI 17-4-MIL™ alloy possesses a relatively high strength and hardness in the annealed condition. The strength and hardness of the material is generally somewhat lower in the H 1150 overaged condition.

To develop further increase in strength, the annealed material is precipitation hardened by heat treatments at 900°F (482°C). Heat treatments above 1075°F (579°C) generally result in material softer than material in the annealed condition. The heat treatments are usually specified as follows:

The precipitation hardening reaction can be driven past peak strength by heat treating at an excessively high temperature or by excessive time at the precipitation hardening temperature. The table on page 3 shows the effect of higher temperature heat treatment. A less dramatic downward shift in strength results from excessively long precipitation hardening times.

The heat treatments used for the ATI 17-4-MIL™ Precipitation Hardening Alloy are summarized below.

Condition	Temperature	Time
H 900	900°F ± 10 (482°C ± 5)	60 min. ± 5 min.
H 925	925°F ± 10 (496°C ± 5)	4 hrs. ± 0.25 hr.
H 1025	1025°F ± 10 (552°C ± 5)	4 hrs. ± 0.25 hr.
H 1075	1075°F ± 10 (579°C ± 5)	4 hrs. ± 0.25 hr.
H 1100	1100°F ± 10 (593°C ± 5)	4 hrs. ± 0.25 hr.
H 1150	1150°F ± 10 (621°C ± 5)	4 hrs. ± 0.25 hr.

WELDING AND BRAZING

The ATI 17-4-MIL™ Precipitation Hardening Alloy is readily welded using conventional inert gas methods used for stainless grades. Preheating is not usually required. Postweld heat treating is needed to produce the various precipitation hardened heat treatment properties.

If matching filler material is used, properties comparable to those of the parent metal can be produced in the weld by postweld precipitation hardening heat treatment.

When a number of welding passes are made, a substantial thermal cycling has been conducted on the material. More uniform mechanical properties can be obtained by solution annealing the material before conducting precipitation hardening heat treatments. The solution anneal has the effect of minimizing the effects of the thermal cycling.

In the case of welding with non-matching filler, an austenitic stainless steel such as 308L or other ductile austenitic should be used. This filler will not produce the precipitation hardening response, however.

FORMING

The tensile data for the ATI 17-4-MIL™ Precipitation Hardening Alloy indicate that the alloy does not possess the high tensile elongation characteristic of the austenitic stainless steels. The material is capable of being mildly formed but is not capable of being severely formed. Forming is more easily accomplished in the overaged (such as H 1150-M from SA 693) condition than in the annealed, condition.

CONTACT INFORMATION

Andrew Nichols
 Director – ATI Defense
 500 Green Street
 Washington, PA 15301
 Phone: 724-229-3741
 Fax: 724-229-3767
 Email: anichols@alleghenystechnologies.com

Larry Martin
 Business Development Manager – ATI Defense
 PO Box 460
 Albany, OR 97321
 Phone: 724-229-3742
 Fax: 724-229-3767
 Email: larry.martin@alleghenystechnologies.com

alleghenystechnologies.com